



Texan Stone LLC



11806 Wilcrest Drive, Suite 202, Houston, TX 77031

Phone: 281-741-0226

India Best Garnet 20-40 Mesh Product Specification

Chemical Analysis		Sieve Analysis Report			
Elements	%	MM	ASTM	Retained(%)	Cum.(%)
SiO ₂	42-43	0.119	+16	0	0
Al ₂ O ₃	15-16	0.850	+20	0	0
Fe ₂ O ₃	32-33	0.710	+25	9-10	9-10
MgO	2-2.5	0.600	+30	42-43	51-53
CaO	4-5	0.500	+35	20-21	71-74
TiO ₂	Absent	0.425	+40	19-20	92-94
LOI	0.32	0.297	+50	8-10	100
Total				100	100

Mineral Composition		Physical Analysis	
Mineral	% by Weight	Test	Result
Garnet	98-99	Specific Gravity	4.2
Ilmenite	0.5-0.7	Bulk Density	2.3 gm/cm ³
Quartz	0.5-0.7	Hardness	8.3 Moh scale
		Conductivity	-
		Chloride	20 ppm

Standard Packing: 1,000 kgs (2,200 lbs.) or 2,000 kgs (4,400 lbs.) top and bottom spouted bulk bags with internal liner