



# Texan Stone LLC

11806 Wilcrest Drive, Suite 202, Houston, TX 77031  
Phone: 281-741-0226 Email: Mani@texanstone.com



## STAR-O-RIGHT

### STAUROLITE CONCENTRATE SPECIFICATION SHEET



#### Chemical and Physical Analysis

<u>Parameters</u>	<u>Typical (%)</u>
Al <sub>2</sub> O <sub>3</sub> +TiO <sub>2</sub>	45 - 51%
SiO <sub>2</sub>	28 - 29%
Quartz	0.5 – 1.0% max.
Respirable Crystalline Silica	Less than 0.01%
Moisture	0.1% - 0.5%
Chloride	6 PPM
Conductivity	70 μS/cm
Color	Dark Brown
Bulk Density	130 lbs./ft <sup>3</sup>
Specific Gravity	3.7 – 3.8
Grain Shape	Sub-angular
Solubility	Insoluble
Hardness	7 – 7.5 Mohs

#### Size Analysis July 2018

<u>Mesh</u>	<u>Microns</u>	<u>Retention (%)</u>	
		<u>Retained</u>	<u>Cumulative</u>
60	250	0.5-1.0	0.5-1
70	210	12-13	12.5-13.5
80	177	42-44	53-56
100	149	28-30	81-85
120	125	12-14	93-97
140	105	2	95 –99
170	88	0.5-1	96-99.5
200	74	0.25	98-100
Pan	-	0.01	100

**Note: Staurolite is a natural product and as such slight variations in the chemical analysis and size distribution should be expected.**

**Comparable to DuPont Starblast XL and Opta Powerblast XC Staurolite.**